IN THE CLAIMS

Please amend the claims as follows:

- 1. Cancelled.
- 2. Cancelled.
- 3. (Currently Amended) The composition of claim 2, in which the Fischer-Tropsch derived white oil has A polystyrene composition or styrene copolymer composition comprising a white oil as a plasticizer, wherein the white oil comprises a Fischer-Tropsch derived oil having a kinematic viscosity at 100 °C of more than 7 mm²/sec.
- 4. (Currently Amended) The composition of claim 2 3, in which the Fischer-Tropsch derived white oil has a content of mineral hydrocarbons with carbon numbers less than 25 of not more than 5% wt and an average molecular weight not less than 480 g/mol.
 - 5-12. Cancelled.
- 13.(Currently Amended) The composition of claim 12 A polystyrene composition or styrene copolymer composition comprising between 0.1 wt% and 10 wt% of a white oil as a plasticizer, wherein the white oil comprises a Fischer-Tropsch derived oil having a Saybolt color greater than +25, a pour point below -10 °C, a content of polar compounds of less than 1 wt%, a content of non-cyclic isoparaffins between 75 wt% and 98 wt%, a kinematic viscosity at 100 °C of more than 2 mm²/sec, , in which the Fischer-Tropsch derived white oil has a content of mineral hydrocarbons with carbon numbers less than 25 of not more than 5 wt%, and an average molecular weight of not less than 480 g/mol.
- 14.(Original) The composition of claim 13, in which the Fischer-Tropsch derived oil has a 5 wt% recovery boiling point above 391 °C.
 - 15-20. Cancelled.